

## Product Data

# Somos<sup>®</sup> ProtoGen 18120

### Description

DSM's Somos<sup>®</sup> ProtoGen 18120 is a liquid, ABS-like photopolymer that produces accurate parts ideal for general purpose applications. Somos<sup>®</sup> ProtoGen resins are the first stereolithography resins to demonstrate different material properties based on machine exposure control. Based on Somos<sup>®</sup> Oxetane<sup>™</sup> chemistry, Somos<sup>®</sup> ProtoGen 18120 offers superior chemical resistance, a wide processing latitude and excellent tolerance to a broad range of temperature and humidity, both during and after the build.

### Applications

This high-temperature resistant, ABS-like photopolymer is used in solid imaging processes, such as stereolithography, to built three-dimensional parts. Somos<sup>®</sup> ProtoGen 18120 provides considerable processing latitude and is ideal for the medical, electronic, aerospace and automotive markets that demand accurate RTV patterns, durable concept models, highly accurate and humidity & temperature resistant parts.

#### TECHNICAL DATA - LIQUID PROPERTIES

Appearance	Translucent
Viscosity	~300 cps @ 30°C
Density	~1.16 g/cm <sup>3</sup> @ 25°C

#### TECHNICAL DATA - OPTICAL PROPERTIES

E <sub>c</sub>	6.73 mJ/cm <sup>2</sup>	[critical exposure]
D <sub>p</sub>	4.57 mils	[slope of cure-depth vs. ln (E) curve]
E <sub>10</sub>	57.0 mJ/cm <sup>2</sup>	[exposure that gives 0.254 mm (.010 inch) thickness]

TECHNICAL DATA							
Mechanical Properties		Somos® ProtoGen 18120 UV Postcure at HOC -2		Somos® ProtoGen 18120 UV Postcure at HOC +3		Somos® ProtoGen 18120 UV & Thermal Postcure	
ASTM Method	Property Description	Metric	Imperial	Metric	Imperial	Metric	Imperial
D638M	Tensile Strength	51.7 - 54.9 MPa	7.5 - 8.0 ksi	56.9 - 57.1 MPa	8.2 - 8.3 ksi	68.8 - 69.2 MPa	9.9 - 10.0 ksi
D638M	Tensile Modulus	2,620 - 2,740 MPa	381 - 397 ksi	2,540 - 2,620 MPa	370 - 380 ksi	2,910 - 2,990 MPa	422 - 433 ksi
D638M	Elongation at Break	6 - 12%	6 - 12%	8 - 12%	8 - 12%	7 - 8%	7 - 8%
D638M	Poisson's Ratio	0.43 - 0.45	0.43 - 0.45	N/A	N/A	0.43	0.43
D790M	Flexural Strength	81.8 - 83.8 MPa	11.9 - 12.2 ksi	83.8 - 86.7 MPa	12.2 - 12.6 ksi	88.5 - 91.5 MPa	13.2 ksi
D790M	Flexural Modulus	2,360 - 2,480 MPa	343 - 359 ksi	2,400 - 2,450 MPa	350 - 355 ksi	2,330 - 2,490 MPa	361 ksi
D2240	Hardness (Shore D)	84 - 85	85 - 87	N/A	N/A	87 - 88	87 - 88
D256A	Izod Impact (Notched)	0.14 - 0.26 J/m	0.26 - 0.49 ft-lb/in	N/A	N/A	0.13 - 0.25 J/m	0.24 - 0.47 ft-lb/in
D570-98	Water Absorption	0.77%	0.77%	N/A	N/A	0.75%	0.75%

TECHNICAL DATA					
Thermal/Electrical Properties		Somos® ProtoGen 18120 UV Postcure at HOC -2		Somos® ProtoGen 18120 UV & Thermal Postcure	
ASTM Method	Property Description	Metric	Imperial	Metric	Imperial
E831-05	C.T.E. -40 - 0°C (-40 - 32°F)	65.1 - 68.1 µm/m°C	36.2 - 37.8 µin/in°F	63.7 - 71.8 µm/m°C	35.4 - 39.9 µin/in°F
E831-05	C.T.E. 0 - 50°C (32 - 122°F)	84.7 - 95.3 µm/m°C	47.1 - 52.9 µin/in°F	75.0 - 107.5 µm/m°C	41.7 - 59.7 µin/in°F
E831-05	C.T.E. 50 - 100°C (122 - 212°F)	93.8 - 116.9 µm/m°C	52.1 - 64.9 µin/in°F	99.4 - 111.0 µm/m°C	55.2 - 61.7 µin/in°F
E831-05	C.T.E. 100 - 150°C (212 - 302°F)	147.0 - 155.4 µm/m°C	81.7 - 86.3 µin/in°F	143.4 - 173.3 µm/m°C	79.7 - 96.3 µin/in°F
D150-98	Dielectric Constant 60 Hz	3.4 - 3.5	3.4 - 3.5	3.5 - 3.6	3.5 - 3.6
D150-98	Dielectric Constant 1 KHz	3.3 - 3.4	3.3 - 3.4	3.4 - 3.5	3.4 - 3.5
D150-98	Dielectric Constant 1 MHz	3.1 - 3.2	3.1 - 3.2	3.2 - 3.3	3.2 - 3.3
D149-97A	Dielectric Strength	14.4 - 15.3 kV/mm	365 - 387 V/mil	15.2 - 15.7 kV/mm	386 - 398 V/mil
E1545-00	Tg	71 - 86°C	160 - 187°F	76 - 94°C	169 - 201°F
D648	HDT @ 0.46 MPa (66 psi)	55 - 58°C	132 - 136°F	95 - 97°C	203 - 207°F
D648	HDT @ 1.81 MPa (264 psi)	48 - 50°C	118 - 123°F	79 - 82°C	175 - 180°F

**DSM Functional Materials**  
**Somos® Materials Group**

**in North America**

1122 St. Charles Street  
Elgin, Illinois 60120  
USA  
Phone: +1.847.697.0400

**in Europe**

Slachthuisweg 30  
3150 XN Hoek van Holland  
The Netherlands  
Phone: +31.174.315.391

**in China**

476 Li Bing Road  
Zhangjiang Hi-Tech Park  
Pudong New Area  
Shanghai 201203, China  
Phone: +86.21.6141.8064

Visit us online at [www.dsmsomos.com](http://www.dsmsomos.com)

NOTICE : Somos® is a registered trademark of Royal DSM N.V. Somos® is an unincorporated subsidiary of DSM Desotech Inc. The information presented herein is based on generally accepted analytical and testing practices and is believed to be accurate. However, DSM Desotech expressly disclaims any product warranties which may be implied including warranties or merchantability and/or fitness for a particular purpose DSM Desotech's products are sold subject to DSM Desotech's standard terms and conditions of sale, copies of which are available upon request. Purchasers are responsible for determining the suitability of the product for its intended use and the appropriate manner of utilizing the product in purchaser's production processes and applications so as to insure safety, quality and effectiveness. Purchasers are further responsible for obtaining necessary patent rights to practice any invention in connection with the use of purchased product and any other product or process. DSM Desotech reserves the right to change specifications of their products without notice. © 2012 DSM IP ASSETS B.V. All rights reserved.